


EcoRoof Traditional 2.32

General description: coloured asphalt shingle



bituminous compound	-		Blown bitumen	
length	EN 544	mm	1000	+/-3
width	EN 544	mm	340	+/-3
thickness	-	mm	3	+/-10%
exposed area	-	mm	145	-

Physical-chemical properties

weight	-	kg/m ²	8,5	+/-8%
mass of the fibreglass mat	-	g/m ²	100	+/-10%
granules single layer	EN 544	g/m ²	1250	+/-20%
mechanical resistance MD/CMD	EN 544	N/ 5 cm	700/450	+/-15%
nail resistance	EN 544	N	120	+/-20%
granules adhesion	EN 544	-g	0,8	+/-0,15

Fire behaviour

classification according	EN 13501-5	B roof (t1)
classification according	EN 13501-1	E

Wrapping

type	polyethylene
shingles for bundle	16
m ² /bundle	2,32
m ² /pallet	185,6

Further info about company, product and roofing instruction on web site www.tegolacanadese.com

Tegola Canadese S.p.A.
Via dell'Industria, 21- 31029 Vittorio V.to (TV) - I -
Tel. +39.0438.91111 - Fax +39.0438.911260
e-mail: info@tegolacanadese.com



Company certified according quality system ISO 9001 and environmental system ISO14001